

DESCRIPTION

Total thickness	EN 428	mm	2.00
Weight	EN 430	g/m ²	2980
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2

PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear Group	EN 649	group	T
Type Binder content	ISO 10581	type	I
Dimensional stability	EN 434	%	≤ 0.4
Residual indentation	EN 433	mm	~ 0.03
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	OK
Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
Color Number	-	-	14