

DESCRIPTION			COMPACT
Total thickness	EN 428	mm	2
	ASTM F386-02	inch	0,08
Wearlayer thickness	EN 429	mm	0,70
	ASTM F410-02	inch	0,03
Weight	EN 430	g/sq.m	2635
	-	lbs/sq.ft	0,54
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	25
	-	feet - inch	82'
CLASSIFICATION			
Norm / Product specification	-	-	EN 649
	ASTM F1303-04	-	in progress
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance: Ramp test	DIN 51 130	class	R11
Slip resistance: Pendulum test (1)	BS 7976-2	PTV	> 36
Surface Roughness	µm	Rz	> 20
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649 - EN 651	-	T
Type binder content	ISO 10582	typ	I
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (requirement)	EN 433	mm	≤ 0.10
Residual indentation (measure)	EN 433	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	ProtecSol Control
Chemical products resistance	EN 423	-	OK
Anti-bacterial activity (E. coli - S. aureus - MRSA) (2)	ISO 22196		> 99 % inhibits growth
ENVIRONMENT / INDOOR QUALITY AIR			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 70
Certification			Floorscore™
CE MARKING			
	EN 14041		 

(1) The RRL pendulum test: wet is expressed as a pendulum test Value (PTV) and a Slip Resistance Value (SRV) to show that the test was carried out using a 4S rubber resistor pad in accordance HSE guidance (For lifetime sustainable wet resistance, please refer to Tarasafe ranges).

(2) The implementation of an effective cleaning method is the best defence against infection