



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
PRODUCT DESCRIPTION				
Surface treatment	-	-	-	Protecsol®
Surface complex	-	-	-	D-Max
Foam	-	-	-	CXP HD
Thickness	EN 428	-	mm	9.35
Weight	EN 430	-	kg/m ²	5.4
Length	EN 426	-	lm	26.4 max
Width	EN 426	-	lm	1.5
Impact Protection Index	AC- P90-205	-	%	IPI = 82%
SPORT PROPERTIES				
Shock absorption	EN 14808	≥ 25	%	 P2
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 3
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
CLASSIFICATION				
Fire	EN 13501-1	-	-	 Cfl-s1
Treatment	-	-	-	Sanosol®
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99.9 % inhibits growth
DECLARATION OF PERFORMANCE				
	DOP-005-1018-A	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	INSTALLATION METHODS		
	Gerflor's recommendation	Unit	Results
Dry-Tex™ System 		%	No limit (no dripping water on the slab)

COLOUR RANGE	
 6381 Maple Design  6375 Oak Design  6211 Gold  6038 Terracotta  6159 Pink  6146 Coral  6180 Red  6559 Spring  6557 Forest  6570 Mint Green  2404 London Light Blue  6445 Lagoon  6430 Blue  6431 Teal  6758 Silver Gray  6873 Anthracite  3764 Taupe  6347 Beige  6830 Black	TARAFLEX® SPORT M PERFORMANCE  Customized length

(3) The implementation of an effective cleaning method is the best defence against infection